

View Online at <https://aerobasegroup.com/nsn/5325-00-584-1943>

Cross Sectional Shape:

Rounded corners

Inside Diameter:

Between 1.026 inches and 1.051 inches

Casehardening Indicator:

Not casehardened

Major Thickness:

0.050 inches

Ring Style:

External

Usage Design:

External

Material Hardness Rating:

Between 37.0 rockwell c and 43.0 rockwell c

Strength Rating:

140000.0 pounds per square inch yield

Material:

Copper beryllium alloy, fed qq-c-533 condition ht

Material:

Copper beryllium alloy, fed qq-c-533 condition ht

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T252-g