

View Online at <https://aerobasegroup.com/nsn/5325-00-917-2576>

**Cross Sectional Shape:**

Round

**Inside Diameter:**

1.125 inches

**Casehardening Indicator:**

Not casehardened

**Outside Diameter:**

1.269 inches

**Major Thickness:**

0.072 inches

**End Style:**

90 degree parallel

**Ring Style:**

Straight gap

**Usage Design:**

External

**Material Hardness Rating:**

Between 40.0 rockwell c and 45.0 rockwell c

**Strength Rating:**

287000.0 pounds per square inch tensile

**Special Features:**

Embrittlement relief part should be heated to 375 degrees porm 25 degrees f for 3 hr. Preferably within 4 hr. After plating

**Material:**

Steel, qq-w-470

**Material:**

Steel uns k08500

**Material Specification:**

Qq-w-470 federal specification single material response

**Surface Treatment:**

Cadmium

**Surface Treatment:**

Cadmium plated

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

T252-g