

View Online at <https://aerobasegroup.com/nsn/5325-01-026-3244>

Cross Sectional Shape:

Rectangular

Casehardening Indicator:

Not casehardened

Outside Diameter:

Between 1.368 inches and 1.413 inches

Major Thickness:

Between 0.048 inches and 0.052 inches

Ring Style:

Internal

Usage Design:

Internal

Material Hardness Rating:

Between 44.0 rockwell c and 51.0 rockwell c

Material:

Steel, ams 5520

Material:

Steel comp 632

Material Specification:

Ams 5520 assn standard single material response

Surface Treatment:

Passivate

Special Test Features:

Special quality control testing

Surface Treatment:

Passivated, qq-p-35

Test Data Document:

81349-mil-p-23199 specification (includes engineering type bulletins, brochures, etc., that reflect specification type data in specification format; excludes commercial catalogs, industry directories, and similar trade publications, reflecting general type data on certain environmental and performance requirements and test conditions that are shown as "typical", "average", "", etc.).

Specification Or Standard:

1 type and 1 class

Departure From Cited Document:

As differentiated by material which must conform to ships parts control center special quality control provisions

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

T252-g