Retaining Ring - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5325-01-197-2756

Cross Sectional Shape:

Rectangular

Inside Diameter:

Between 0.629 inches and 0.642 inches

Casehardening Indicator:

Not casehardened

Outside Diameter:

Between 0.719 inches and 0.732 inches

Major Thickness:

Between 0.0165 inches and 0.0195 inches

Ring Style:

Special

Usage Design:

Internal

Strength Rating:

255000.0 pounds per square inch tensile

Special Features:

Special gvernment inspection

Material:

Steel, sae 1070 or steel, sae 1072 or steel, sae 1074 or steel, sae 1075 or steel, sae 1078 or steel, sae 1080 or steel, sae 1084 or steel, sae 1085 or steel, sae 1086 or steel, sae 1090

Material:

Steel, sae 1070 or steel comp 1572 or steel comp 1074 or steel comp 1075 or steel comp 1078 or steel comp 1080 or steel comp 1084 or steel comp 1085 or steel comp 1086 or steel comp 1090

Material Specification:

Sae 1072 assn standard 2nd material response and sae 1074 assn standard 3rd material response and sae 1075 assn standard 4th material response and sae 1078 assn standard 5th material response and sae 1080 assn standard 6th material response and sae 1084 assn standard 7th material response and sae 1085 assn standard 8th material response and sae 1086 assn standard 9th material response and sae 1090 assn standard 10th material response

Surface Treatment:

Cadmium and chromate

Surface Treatment Specification:

Qq-p-416, type 2, class 2 federal specification single treatment response

Surface Treatment:

Cadmium, qq-p-416, type 2, class 2

Shelf Life:

N/a

Unit Of Measure:

Demilitarization:

No

Fiig:

T252-g