NSN 5325-01-230-5278

Retaining Ring - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5325-01-230-5278

| Cross Sectional Shape: |
|---|
| Beveled one inside corner |
| Inside Diameter: |
| Between 2.745 inches and 2.795 inches |
| Casehardening Indicator: |
| Not casehardened |
| Minor Thickness: |
| Between 0.069 inches and 0.073 inches |
| Major Thickness: |
| Between 0.090 inches and 0.096 inches |
| Ring Style: |
| External |
| Usage Design: |
| External |
| Material Hardness Rating: |
| Between 47.0 rockwell c and 52.0 rockwell c |
| Material: |
| Steel, federal standard 66, comp 1070 or steel, federal standard 66, comp 1074 or steel, federal standard 66, comp 1078 or steel, |
| federal standard 66, comp 1080 or steel, federal standard 66, comp 1084 or steel, federal standard 66, comp 1085 or steel, federal |
| standard 66, comp 1086 or steel, federal standard 66, comp 1090 |
| Material: |
| Steel comp 1070 or steel comp 1074 or steel comp 1078 or steel comp 1080 or steel comp 1070 or steel comp 1085 or steel comp 1086 or |
| steel comp 1090 |
| Material Specification: |
| Fed standard 66, comp 1070 federal standard 1st material response and federal standard 66, comp 1074 federal standard 2nd material |
| response and federal standard 66, comp 1078 federal standard 3rd material response and federal standard 66, comp 1080 federal standard |
| 4th material response and federal standard 66, comp 1084 federal standard 5th material response and federal standard 66, comp 1085 |
| federal standard 6th material response and federal standard 66, comp 1086 federal standard 7th material response and federal standard 66, |
| comp 1090 federal standard 8th material response |
| Surface Treatment: |
| Phosphate zinc |
| Surface Treatment Specification: |
| Dod-p-16232, type z, class 2 def stan/spec single treatment response |
| Surface Treatment: |
| Phosphate, dod-p-16232, type z, class 2 |
| Shelf Life: |
| N/a |
| Unit Of Measure: |
| |
| Demilitarization: |
| No |

Fiig: T252-g