NSN 5325-01-270-2898

Retaining Ring - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5325-01-270-2898

Cross Sectional Shape:
Rectangular
Inside Diameter:
Between 0.107 inches and 0.113 inches
Casehardening Indicator:
Not casehardened
Outside Diameter:
0.320 inches
Major Thickness:
Between 0.033 inches and 0.037 inches
Ring Style:
External
Usage Design:
External
Material Hardness Rating:
Between 51.0 rockwell c and 55.0 rockwell c
Material:
Steel, sae 1060 or steel, sae 1064 or steel, sae 1065 or steel, sae 1070 or steel, sae 1074 or steel, sae 1078 or steel, sae 1080 or steel,
sae 1084 or steel, sae 1085 or steel, sae 1086 or steel, sae 1090
Material:
Steel comp 1060 or steel comp 1064 or steel comp 1065 or steel, sae 1070 or steel comp 1074 or steel comp 1078 or steel comp 1080 or
steel comp 1084 or steel comp 1085 or steel comp 1086 or steel comp 1090
Material Specification:
Sae 1060 assn standard 1st material response and sae 1064 assn standard 2nd material response and sae 1065 assn standard 3rd material
response and sae 1074 assn standard 5th material response and sae 1078 assn standard 6th material response and sae 1080 assn
standard 7th material response and sae 1084 assn standard 8th material response and sae 1085 assn standard 9th material response and
sae 1086 assn standard 10th material response and sae 1090 assn standard 11th material response
Surface Treatment:
Phosphate zinc
Surface Treatment Specification:
Dod-p-16232, type z, class 2 def stan/spec single treatment response
Surface Treatment:
Phosphate, dod-p-16232, type z, class 2
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
T252-a