Retaining Ring - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5325-01-386-6435

Cross Sectional Shape:

Rectangular

Inside Diameter:

Between 1.026 inches and 1.051 inches

Casehardening Indicator:

Not casehardened

Major Thickness:

Between 0.048 inches and 0.052 inches

Ring Style:

External bowed

Usage Design:

External

Material Hardness Rating:

Between 48.0 rockwell c and 53.0 rockwell c

Strength Rating:

150000.0 pounds per square inch tensile

End Play Takeup:

0.085 inches

Material:

Steel, sae 1060 or steel, sae 1064 or steel, sae 1065 or steel, sae 1070 or steel, sae 1074 or steel, sae 1078 or steel, sae 1080 or steel, sae 1084 or steel, sae 1086 or steel, sae 1080 or steel, sae 10

Material:

Steel comp 1060 or steel comp 1064 or steel comp 1065 or steel, sae 1070 or steel comp 1074 or steel comp 1078 or steel comp 1080 or steel comp 1085 or steel comp 1086 or steel comp 1090

Material Specification:

Sae 1060 assn standard 1st material response and sae 1064 assn standard 2nd material response and sae 1065 assn standard 3rd material response and sae 1074 assn standard 5th material response and sae 1078 assn standard 6th material response and sae 1080 assn standard 7th material response and sae 1084 assn standard 8th material response and sae 1085 assn standard 9th material response and sae 1086 assn standard 10th material response and sae 1090 assn standard 11th material response

Surface Treatment:

Zinc and chromate

Surface Treatment:

Zinc, astm b633, type 2

Specification Data:

96906-ms16628 government specification

Shelf Life:

N/a

Unit Of Measure:

Demilitarization:

No

Fiig:

T252-g