NSN 5330-00-061-5564Preformed Packing - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5330-00-061-5564
Cross Sectional Shape:
O-ring
Tempurature Rating:
-30.0 degrees fahrenheit and 250.0 degrees fahrenheit
Cross Section Outside Diameter:
Between 0.067 inches and 0.073 inches
Cross-sectional Height:
Between 0.067 inches and 0.073 inches
Center Hole Diameter:
Between 1.358 inches and 1.370 inches
Peripheral Diameter:
Between 1.485 inches and 1.523 inches
Elongation Percentage:
331
Hardness Rating:
65.0 shore durometer a and 75.0 shore durometer a
Material:
Rubber butadiene-acrylonitrile class nbr
Material Specification:
Astm d2000 2bg715be1e3f1 assn standard single material response
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:

A032a0