

View Online at <https://aerobasegroup.com/nsn/5330-00-111-3721>

Cross Sectional Shape:

O-ring

Temperature Rating:

-20.0 degrees fahrenheit and 400.0 degrees fahrenheit

Cross Section Outside Diameter:

Between 0.135 inches and 0.143 inches

Cross-sectional Height:

Between 0.135 inches and 0.143 inches

Center Hole Diameter:

Between 13.954 inches and 14.014 inches

Peripheral Diameter:

14.262 inches

Elongation Percentage:

125

Hardness Rating:

70.0 shore durometer a and 80.0 shore durometer a

Material:

Rubber fluorocarbon class fpm

Material Specification:

Ams-7278 assn standard single material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A032a0