

View Online at <https://aerobasegroup.com/nsn/5330-00-472-2713>

Cross Sectional Shape:

Rectangular metal

Outside Diameter:

Between 0.480 inches and 0.520 inches

Aperture Diameter:

Between 0.320 inches and 0.340 inches

Cross-sectional Thickness:

0.030 inches

Material:

Copper alloy 110

Material Specification:

Ams 4500 assn standard single material response

Special Test Features:

Anneal for 1/2 hour at 1200 degrees f air cool hardness rating after annealing 35 maximum 15 t scale

Style Designator:

Circular

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A032a0