## NSN 5330-00-595-6245

Preformed Packing - Page 1 of 1



)-595-6245

View Online at https://aerobasegroup.com/nsn/5330-00
Cross Sectional Shape:
O-ring
Tempurature Rating:
-40.0 degrees fahrenheit and 250.0 degrees fahrenheit
Cross Section Outside Diameter:
Between 0.205 inches and 0.215 inches
Cross-sectional Height:
Between 0.205 inches and 0.215 inches
Center Hole Diameter:
Between 3.585 inches and 3.615 inches
Peripheral Diameter:
Between 3.982 inches and 4.058 inches
Elongation Percentage:
331
Hardness Rating:
65.0 shore durometer a and 75.0 shore durometer a
Material:
Rubber butadiene-acrylonitrile class nbr
Material Specification:
N674-70 fscm 02697 mfr ref single material response
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:

A032a0