

View Online at <https://aerobasegroup.com/nsn/5330-00-789-0771>

Elongation Percentage:

500

Hardness Rating:

35.0 shore durometer a and 45.0 shore durometer a

Material:

Rubber chloroprene class cr

Material Specification:

Mil-s-6855, cl 2, gr 40 military specification single material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A032a0

Mil-std (military Standard):

Mil-s-6855 spec.