

View Online at <https://aerobasegroup.com/nsn/5330-00-927-4544>

**Temperature Rating:**

-85.0 degrees fahrenheit and 401.0 degrees fahrenheit

**Elongation Percentage:**

125

**Hardness Rating:**

65.0 shore durometer a and 75.0 shore durometer a

**Material:**

Rubber silicone class q and steel comp 302

**Material Specification:**

Ams 3304 assn standard 1st material response and mil-s-5059, annealed military specification 2nd material response

**Surface Treatment:**

Anodize

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A032a0

**Mil-std (military Standard):**

Mil-s-5059 spec.