

View Online at <https://aerobasegroup.com/nsn/5330-01-078-8857>

Cross Sectional Shape:

Solid single or composition

Outside Diameter:

Between 1.042 inches and 1.052 inches

Aperture Diameter:

Between 0.912 inches and 0.922 inches

Cross-sectional Thickness:

Between 0.050 inches and 0.070 inches

Elongation Percentage:

125

Hardness Rating:

35.0 shore durometer a and 45.0 shore durometer a

Material:

Rubber fluorosilicone class fq

Material Specification:

Mil-r-25988, type 2, cl 1, gr 40 military specification single material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A032a0

Mil-std (military Standard):

Mil-r-25988 spec.