

View Online at <https://aerobasegroup.com/nsn/5330-01-108-0681>

Cross Sectional Shape:

O-ring

Temperature Rating:

-30.0 degrees fahrenheit and 250.0 degrees fahrenheit

Cross-sectional Height:

Between 0.205 inches and 0.215 inches

Center Hole Diameter:

Between 2.340 inches and 2.360 inches

Peripheral Diameter:

Between 2.742 inches and 2.798 inches

Elongation Percentage:

331

Hardness Rating:

65.0 shore durometer a and 75.0 shore durometer a

Criticality Code Justification:

Zzzy

Material:

Rubber butadiene-acrylonitrile class nbr

Material Specification:

N674-70 fscm 02697 mfr ref single material response

Special Test Features:

Special quality control testing

Test Data Document:

81349-mil-p-23199 specification (includes engineering type bulletins, brochures, etc., that reflect specification type data in specification format; excludes commercial catalogs, industry directories, and similar trade publications, reflecting general type data on certain environmental and performance requirements and test conditions that are shown as "typical", "average", "", etc.).

Reference Number Differentiating Characteristics:

As differentiated by material which must conform to ships parts control center special quality control provisions and certified free from mercury contamination

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A032a0