NSN 5330-01-133-8651

Preformed Packing - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5330-01-133-8651

Cross Sectional Shape:
O-ring
Tempurature Rating:
-55.0 degrees fahrenheit and 225.0 degrees fahrenheit
Cross Section Outside Diameter:
Between 0.067 inches and 0.073 inches
Cross-sectional Height:
Between 0.067 inches and 0.073 inches
Center Hole Diameter:
Between 0.667 inches and 0.685 inches
Peripheral Diameter:
Between 0.801 inches and 0.831 inches
Elongation Percentage:
582
Hardness Rating:
50.0 shore durometer a
Material:
Rubber butadiene-acrylonitrile class nbr
Material Specification:
Ams 3205 assn standard single material response
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiia:

A032a0