## NSN 5330-01-165-1113

Preformed Packing - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5330-01-165-1113

view Offinite at https://aerobasegroup.com/nsi//5550-01-100
Cross Sectional Shape:
O-ring
Tempurature Rating:
-40.0 degrees fahrenheit and 250.0 degrees fahrenheit
Cross Section Outside Diameter:
Between 0.269 inches and 0.281 inches
Cross-sectional Height:
Between 0.269 inches and 0.281 inches
Center Hole Diameter:
Between 7.063 inches and 7.153 inches
Peripheral Diameter:
Between 7.601 inches and 7.715 inches
Elongation Percentage:
160
Hardness Rating:
90.0 shore durometer a
Material:
Rubber butadiene-acrylonitrile class nbr
Material Specification:
Mil-r-15624 military specification single material response
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
A032a0
Mil-std (military Standard):

Mil-r-15624 spec.