## NSN 5330-01-181-8105

Preformed Packing - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5330-01-181-8105

Cross Sectional Shape:
O-ring
Tempurature Rating:
-40.0 degrees fahrenheit and 500.0 degrees fahrenheit
Cross-sectional Height:
Between 0.100 inches and 0.106 inches
Center Hole Diameter:
Between 3.937 inches and 4.002 inches
Hardness Rating:
70.0 shore durometer a and 80.0 shore durometer a
Material:
Rubber fluorocarbon class fpm
Material Specification:
Mil-r-25897 military specification single material response
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
A032a0
Mil-std (military Standard):
Mil-r-25897 spec.