

View Online at <https://aerobasegroup.com/nsn/5330-01-222-3507>

Cross-sectional Height:

Between 0.067 inches and 0.073 inches

Center Hole Diameter:

Between 0.234 inches and 0.244 inches

Peripheral Diameter:

0.379 inches

Elongation Percentage:

125

Hardness Rating:

75.0 shore durometer a

Criticality Code Justification:

Zzzw

Material:

Rubber fluorocarbon class fpm

Departure From Cited Document:

Material will be in accordance with ships parts control center activity hx quality control, manufacturing and testing specifications

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A032a0