# NSN 5330-01-290-9411

Preformed Packing - Page 1 of 1

View Online at https://aerobasegroup.com/nsn/5330-01-290-9411



# Cross Sectional Shape:

O-ring

# **Tempurature Rating:**

-5.0 degrees celsius and 205.0 degrees celsius

# **Cross Section Outside Diameter:**

Between 0.100 inches and 0.106 inches

#### **Cross-sectional Height:**

Between 0.100 inches and 0.106 inches

#### **Center Hole Diameter:**

Between 1.659 inches and 1.689 inches

#### **Peripheral Diameter:**

Between 1.859 inches and 1.901 inches

#### End Application:

2840-99-645-9394

Hardness Rating:

70.0 shore durometer a and 80.0 shore durometer a

#### **Operating Medium:**

Fluid, high temperature

Color:

Brown

## Material:

Rubber polymethylene-perfluoroalkylene class fkm

## Material Specification:

Ams7280 assn standard single material response or astm d2000/sae j200 2hk715a1-10b37b38ef31eo78f18z1 assn standard single material

response

#### **Relationship To Similar Equipment:**

SIMI-LA-RTO-NSN5

## Type/model Designation:

Rb199mk101/103/104

#### **Reference Number Differentiating Characteristics:**

As diff by specification k2617 hte7300 performance rqmt tornado aircraft engine model rb199

## Shelf Life:

N/a

#### Unit Of Measure:

---

#### Demilitarization:

No

Fiig:

A032a0