

View Online at <https://aerobasegroup.com/nsn/5330-01-321-8403>

Cross Sectional Shape:

Circular

Nonmetallic Hardness Rating:

35.0 shore durometer a and 45.0 shore durometer a

Tempurature Rating:

-80.0 degrees fahrenheit and 425.0 degrees fahrenheit

Length:

Between 319.500 inches and 320.500 inches

Surface Condition:

Smooth both sides

Cross Section Outside Diameter:

Between 0.441 inches and 0.447 inches

Special Features:

Gasket cross scction shall be continuous at seam no more than one seam is permissible; joined seam tensile strength and ultimate elongation before and after oven aging shall be not less than 80 percent of the requirements specified on zz-r-765 and tested per fed-std-601, method 4311

Material:

Silicone rubber, zz-r-765, class 2b, grade 40

Material:

Rubber silicone class q

Material Specification:

Zz-r-765, class 2b, grade 40 federal specification single material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A26800