NSN 5330-01-321-8403

Rubber Round Section - Page 1 of 1

A26800



View Online at https://aerobasegroup.com/nsn/5330-01-321-8403

| View Online at https://aerobasegroup.com/nsn/5330-01-321-8403 |
|---|
| Cross Sectional Shape: |
| Circular |
| Nonmetallic Hardness Rating: |
| 35.0 shore durometer a and 45.0 shore durometer a |
| Tempurature Rating: |
| -80.0 degrees fahrenheit and 425.0 degrees fahrenheit |
| Length: |
| Between 319.500 inches and 320.500 inches |
| Surface Condition: |
| Smooth both sides |
| Cross Section Outside Diameter: |
| Between 0.441 inches and 0.447 inches |
| Special Features: |
| Gasket cross scction shall be continuous at seam no more than one seam is permissible; joined seam tensile strength and ultimate |
| elongation before and after oven aging shall be not less than 80 percent of the requirements specified on zz-r-765 and tested per |
| fed-std-601, method 4311 |
| Material: |
| Silicone rubber, zz-r-765, class 2b, grade 40 |
| Material: |
| Rubber silicone class q |
| Material Specification: |
| Zz-r-765, class 2b, grade 40 federal specification single material response |
| Shelf Life: |
| N/a |
| Unit Of Measure: |
| |
| Demilitarization: |
| No |
| Fiig: |