

View Online at <https://aerobasegroup.com/nsn/5330-01-321-8403>

**Cross Sectional Shape:**

Circular

**Nonmetallic Hardness Rating:**

35.0 shore durometer a and 45.0 shore durometer a

**Tempurature Rating:**

-80.0 degrees fahrenheit and 425.0 degrees fahrenheit

**Length:**

Between 319.500 inches and 320.500 inches

**Surface Condition:**

Smooth both sides

**Cross Section Outside Diameter:**

Between 0.441 inches and 0.447 inches

**Special Features:**

Gasket cross scction shall be continuous at seam no more than one seam is permissible; joined seam tensile strength and ultimate elongation before and after oven aging shall be not less than 80 percent of the requirements specified on zz-r-765 and tested per fed-std-601, method 4311

**Material:**

Silicone rubber, zz-r-765, class 2b, grade 40

**Material:**

Rubber silicone class q

**Material Specification:**

Zz-r-765, class 2b, grade 40 federal specification single material response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A26800