

View Online at <https://aerobasegroup.com/nsn/5330-01-379-5172>

Cross-sectional Height:

Between 0.112 inches and 0.120 inches

Center Hole Diameter:

Between 0.915 inches and 0.933 inches

Peripheral Diameter:

1.156 inches

Elongation Percentage:

125

Hardness Rating:

90.0 shore durometer a

Criticality Code Justification:

Zzzw

Material:

Rubber fluorocarbon class fpm

Departure From Cited Document:

Material will be in accordance with ships parts control center activity hx quality control, manufacturing and testing specifications

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A032a0