

View Online at <https://aerobasegroup.com/nsn/5331-01-576-2781>

**Temperature Rating:**

-85.0 degrees fahrenheit and 400.0 degrees fahrenheit

**Cross-sectional Height:**

Between 0.148 inches and 0.222 inches

**Center Hole Diameter:**

Between 217.686 inches and 229.314 inches

**Hardness Rating:**

70.0 shore durometer a

**Special Features:**

Due to limited physical strength, poor abrasion resistance, and high friction characteristics, fluorosilicone elastomers are not generally recommended for dynamic sealing, and they are also not recommended for exposure to brake fluids, hydrazine, or ketones

**Color:**

Black

**Material:**

Rubber fluorosilicone class fq

**Material Specification:**

Astm d2000/sae 3200 type, class fk assn standard single material response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A510x0