

View Online at <https://aerobasegroup.com/nsn/5340-00-345-3826>

**Special Features:**

Material is per astm a322 or a331, 8620, 94b17, 4620; surface treatment is per mil-p-16232, type z or m, class 1; heat treatment: carburize at 1575-1600 deg. F., from 0.008 to 0.010 in. Depth, oil quench, temper 30 min. At approx. 350 deg. F. To rockwell hardness 15n, 89min.; 0.950 in. Lg.; 0.324 in. W.; 0.311 in. High; hole dia. Is 0.080 in.

**Material:**

Steel

**Surface Treatment:**

Phosphate manganese or phosphate zinc

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli

**Fiig:**

A10600