

View Online at <https://aerobasegroup.com/nsn/5340-00-715-7698>

General Description:

Steel, 6620, astm a322 or a331; carburize at 1575-1625 deg. F. To case depth of 0.005-0.008 in., oil quench, temper 30 min. At 350 deg. F.; manganese phosphate, type m, or zinc phosphate, typez, per mil-p-16232, class 1; 1.750 in. Lg.; 1.411 in. W.; 0.812 in. High; 1 hole 0.393 in. Dia.; 2 holes threaded to 0.250-28unf-2b; 1 hole 0.339 in. Dia.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No