

View Online at <https://aerobasegroup.com/nsn/5340-00-945-9768>

**Length:**

2.490 inches

**Width:**

2.382 inches

**Special Features:**

Additional matl info: steel astm a109-carbon 17 to 24 pct; precision casting: steel, investment casting, comp 1c8620 specification mil-s-22141; heat treat: carburize at 1675 degrees f, to a case depth of 0.007-0.015 in.; cool in furnace; harden at 1550 degrees for 1 hr; oil quench; temper at 350 dewg f for 1 hr to 15n87-91; heat treat method is for guidance exc. That case depth and tempering time at temperature are mandatory; 0.550 in. Ht

**Material:**

Steel

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A10600