

View Online at <https://aerobasegroup.com/nsn/5340-01-133-5417>

General Description:

Steel carbon 1045 through 1095 type optl, no.5, spec astm a684; quench and temper to 47 through 52 hrc; after heat treatment, decarburization (free ferrite plus partial) 0.003 max

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A23900