

View Online at <https://aerobasegroup.com/nsn/5340-01-327-9979>

End Application:

Amraam lau 128a f-15

Operation Method:

Air

Special Features:

Item's oa hght 1.402 to 1.404 in.; matl cres ams 5643 type 17-4ph, heat treated iaw mil-h-6875 to condition h1025, cl d, passivated iaw qq-p-35, type 2 or 8, nibron coated iaw ams 2433, 0.0016 to 0.0020 in. Thk and post baked @ 675 degrees porm 35 degrees for 90 minutes, no coating allowed in the hole; item's oa hght 1.402 to 1.404 in.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A07200