

View Online at <https://aerobasegroup.com/nsn/5340-01-331-6971>

End Application:

Amraam lau-128a

Special Features:

3item is heat treated to condition h1025 tensile strength 145 ksi mil-h-6875 cl d; surface texture c-12 maximum per nas 823 is not applicable when using alternate matl nor is the inspection reqmts of rejection due to hot tears or cold shuts

Material:

Stainless steel or steel comp 321

Surface Treatment:

Passivate

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A10600