

View Online at <https://aerobasegroup.com/nsn/5360-00-536-1548>

General Description:

Material 720 alloy annealed 0.018 in. Draw to 0.015 in., heat treat at 750 degrees f 2 hours, passivate finish, 18.50 mm approx developed lg, 10.00 mm o/a formed lg

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No