

View Online at <https://aerobasegroup.com/nsn/5365-00-076-1419>

General Description:

Material, steel cres ams5643; heat treatment, mil-h-6875 quench and temperto hardness specified; final protectivefinish, 4.1 plus 5.4.1 of mil-std-171; embrittlement relief, part shall be heated at a temp between plus 350 deg.To plus 400 deg.F for 5 hours min then aircool to room temp

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No