

View Online at <https://aerobasegroup.com/nsn/5510-00-167-6851>

Species-grade And Grading Association:

Any acceptable 2 common northeastern lumber manufacturers association or any acceptable 2 common northern hardwood and pine manufacturers association or redwood select redwood inspection service or pine, southern no. 1 boards southern pine inspection bureau or any acceptable construction west coast lumber inspection bureau or any acceptable 2 common western wood products association

Moisture Content Retention Percentage:

19.0

Random Length:

6 feet and longer, permitting 10 pct 6-9 feet and requiring 30 pct 14 feet or longer

Width-location And Measuring Method:

6.000 inches specified

Measuring Method And Length:

6.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

1.000 inches specified

Typical Wood Products Use:

High quality construction, sheathing and blocking

Supplementary Features:

Unit of issue-bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

3 table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0