

View Online at <https://aerobasegroup.com/nsn/5510-00-167-6852>

Species-grade And Grading Association:

Cedar, northern white no. 2 northeastern lumber manufacturers association or cedar, western red construction west coast lumber inspection bureau or cedar, western red 2 common western wood products association or cedar, western red construction western wood products association or douglas fir construction west coast lumber inspection bureau or douglas fir 2 common western wood products association or douglas fir construction western wood products association or fir, balsam no. 2 northeastern lumber manufacturers association or fir, balsam 2 common northern hardwood and pine manufacturers association or fir, subalpine 2 common western wood products association or fir, subalpine construction western wood products association or hem-fir construction west coast lumber inspection bureau or hem-fir 2 common western wood products association or hem-fir construction western wood products association or hemlock, eastern no. 2 northeastern lumber manufacturers association or hemlock, eastern 2 common northern hardwood and pine manufacturers association or hemlock, mountain construction west coast lumber inspection bureau or hemlock, mountain 2 common western wood products association or hemlock, mountain construction western wood products association or larch 2 common western wood products association or larch construction western wood products association or pine, eastern white premium northeastern lumber manufacturers association or pine, eastern white 2 common northern hardwood and pine manufacturers association or pine, idaho white 2 common western wood products association or pine, idaho white construction western wood products association or pine, idaho white sterling western wood products association or pine, jack no. 2 northeastern lumber manufacturers association or pine, jack 2 common northern hardwood and pine manufacturers association or pine, lodgepole 2 common western wood products association or pine, lodgepole construction western wood products association or pine, pitch no. 2 northeastern lumber manufacturers association or pine, ponderosa 2 common western wood products association or pine, ponderosa construction western wood products association or pine, norway premium northeastern lumber manufacturers association or pine, norway no. 2 northern hardwood and pine manufacturers association or pine, southern no. 1 boards southern pine inspection bureau or pine, sugar 2 common western wood products association or pine, sugar construction western wood products association or redwood select redwood inspection service or spruce, eastern no. 2 northeastern lumber manufacturers association or spruce, eastern 2 common northern hardwood and pine manufacturers association or spruce, engelmann 2 common western wood products association or spruce, engelmann construction western wood products association or spruce, sitka construction west coast lumber inspection bureau or tamarack no. 2 northeastern lumber manufacturers association or tamarack 2 common northern hardwood and pine manufacturers association

Moisture Content Retention Percentage:

19.0

Random Length:

6 feet and longer, permitting 10 pct 6-9 feet and requiring 30 pct 14 feet or longer

Width-location And Measuring Method:

8.000 inches specified

Measuring Method And Length:

6.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

1.000 inches specified

Typical Wood Products Use:

High quality construction, sheathing and blocking

Supplementary Features:

Unit of issue-board foot

Specification Data:

81348-mm-l-751 government specification

Shelf Life:

N/a