

View Online at <https://aerobasegroup.com/nsn/5510-00-220-1539>

Random Width:

5 in. And wider, per applicable association standard

Species-grade And Grading Association:

Douglas fir factory select western wood products association or douglas fir select shop west coast lumber inspection bureau or pine, eastern white factory select northern hardwood and pine manufacturers association or pine, idaho white factory select western wood products association or pine, ponderosa factory select western wood products association or pine, norway factory select northern hardwood and pine manufacturers association or pine, sugar factory select western wood products association or spruce, eastern factory select northern hardwood and pine manufacturers association or spruce, sitka select shop west coast lumber inspection bureau

Moisture Content Retention Percentage:

15.0

Random Length:

4 ft and longer, permitting 25 pct 4-8 ft lengths

Width-location And Measuring Method:

5.000 inches random

Measuring Method And Length:

4.000 feet random

Surface Condition Degree:

Rough-unsanded full length

Thickness-location And Measuring Method:

1.500 inches specified

Typical Wood Products Use:

Cutting grade for remanufacturing purposes such as door and window stock, patterns, furniture and templates

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0