

View Online at <https://aerobasegroup.com/nsn/5510-00-220-1652>

**Random Width:**

4 or 5 in. And wider per assn std

**Species-grade And Grading Association:**

Any acceptable no. 1 cuts northeastern lumber manufacturers association or any acceptable no. 1 shop northern hardwood and pine manufacturers association or any acceptable no. 1 shop west coast lumber inspection bureau or any acceptable no. 1 shop western wood products association or pine, southern no. 1 shop southern pine inspection bureau or redwood no. 1 shop redwood inspection service

**Moisture Content Retention Percentage:**

15.0

**Random Length:**

4 ft and longer maximum of 25 pct to be 4-8 ft

**Width-location And Measuring Method:**

4.000 inches random

**Measuring Method And Length:**

4.000 feet random

**Surface Condition Degree:**

Rough-unsanded full length

**Thickness-location And Measuring Method:**

2.000 inches specified

**Typical Wood Products Use:**

Cutting grade for remanufacturing purposes such as door and window stock, patterns, furniture and templates

**Special Features:**

50 to 70 pct clear cuttings

**Supplementary Features:**

Unit of issue 8ft

**Specification Data:**

81348-mm-l-751 government specification

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0