

View Online at <https://aerobasegroup.com/nsn/5510-00-220-6168>

Species-grade And Grading Association:

Cedar, western red construction west coast lumber inspection bureau or douglas fir construction west coast lumber inspection bureau or fir construction west coast lumber inspection bureau or hemlock, western construction west coast lumber inspection bureau or spruce, sitka construction west coast lumber inspection bureau and douglas fir no. 1 western wood products association or cedar, western red no. 1 western wood products association or fir no. 1 western wood products association or spruce, engelmann no. 1 western wood products association or pine, idaho white colonial western wood products association or larch no. 1 western wood products association or pine, lodgepole c ship decking western wood products association or pine, ponderosa no. 1 western wood products association or pine, sugar no. 1 western wood products association and pine, southern c ship decking southern pine inspection bureau and redwood select heart redwood inspection service and spruce, eastern no. 1 northeastern lumber manufacturers association and spruce, eastern no. 1 northern hardwood and pine manufacturers association

Random Length:

8 feet and longer, permitting 5 pct 8 and 9 feet and requiring 50 pct 14 feet or longer

Width-location And Measuring Method:

6.000 inches specified

Measuring Method And Length:

8.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

3.000 inches specified

Typical Wood Products Use:

High quality construction and industrial uses, heavy framing and decking

Supplementary Features:

Unit of issue, board foot

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0