

View Online at <https://aerobasegroup.com/nsn/5510-00-220-6170>

**Species-grade And Grading Association:**

Douglas fir construction west coast lumber inspection bureau or spruce, sitka construction west coast lumber inspection bureau or hemlock, western construction west coast lumber inspection bureau or cedar, western red construction west coast lumber inspection bureau or fir construction west coast lumber inspection bureau and douglas fir no. 1 western wood products association or spruce, engelmann no. 1 western wood products association or pine, idaho white colonial western wood products association or larch no. 1 western wood products association or pine, lodgepole no. 1 western wood products association or pine, ponderosa no. 1 western wood products association or pine, sugar no. 1 western wood products association or cedar, western red no. 1 western wood products association or fir no. 1 western wood products association and spruce, eastern no. 1 northern hardwood and pine manufacturers association and spruce, eastern no. 1 northeastern lumber manufacturers association and redwood select heart redwood inspection service and pine, southern no. 1 southern pine inspection bureau

**Random Length:**

8 feet and longer, permitting 5 pct 8 and 9 feet and requiring 50 pct 14 feet or longer

**Width-location And Measuring Method:**

8.000 inches specified

**Measuring Method And Length:**

8.000 feet random

**Surface Condition Degree:**

Surfaced four sides

**Thickness-location And Measuring Method:**

3.000 inches specified

**Typical Wood Products Use:**

Structural joists and planks for high quality construction rafters, decking, stringers and heavy crating

**Specification Data:**

81348-mm-l-751 government specification

**Specification Or Standard:**

3 table

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0