

View Online at <https://aerobasegroup.com/nsn/5510-00-220-6214>

**Species-grade And Grading Association:**

Any acceptable no. 2 northeastern lumber manufacturers association or any acceptable standard northeastern lumber manufacturers association or any acceptable no. 2 northern hardwood and pine manufacturers association or any acceptable standard northern hardwood and pine manufacturers association or any acceptable no. 2 redwood inspection service or any acceptable standard redwood inspection service or any acceptable no. 2 southern pine inspection bureau or any acceptable standard southern pine inspection bureau or any acceptable no. 2 west coast lumber inspection bureau or any acceptable standard west coast lumber inspection bureau or any acceptable no. 2 western wood products association or any acceptable standard western wood products association

**Random Length:**

8 feet and longer, permitting 5 pct 8 and 9 feet and requiring 50 pct 14 feet or longer

**Width-location And Measuring Method:**

4.000 inches specified

**Measuring Method And Length:**

8.000 feet random

**Surface Condition Degree:**

Surfaced four sides

**Thickness-location And Measuring Method:**

3.000 inches specified

**Typical Wood Products Use:**

Ordinary construction, boxes, studs, rafters and blocking

**Supplementary Features:**

Unit of issue-bf

**Specification Data:**

81348-mm-l-751 government specification

**Specification Or Standard:**

lii table

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0