

View Online at <https://aerobasegroup.com/nsn/5510-00-220-6218>

Species-grade And Grading Association:

Any acceptable no. 2 northeastern lumber manufacturers association or any acceptable no. 2 northern hardwood and pine manufacturers association or any acceptable no. 2 redwood inspection service or any acceptable no. 2 southern pine inspection bureau or any acceptable no. 2 west coast lumber inspection bureau or any acceptable no. 2 western wood products association

Random Length:

8 feet and longer, permitting 5 pct 8 and 9 feet and requiring 50 pct 14 feet or longer

Width-location And Measuring Method:

8.000 inches specified

Measuring Method And Length:

8.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

3.000 inches specified

Typical Wood Products Use:

General construction, skids and heavy crating

Supplementary Features:

Unit of issue-bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

lii table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0