

View Online at <https://aerobasegroup.com/nsn/5510-00-220-6226>

**Species-grade And Grading Association:**

Cedar, western red no. 2 southern pine inspection bureau or cedar, western red standard west coast lumber inspection bureau or douglas fir no. 2 southern pine inspection bureau or douglas fir standard west coast lumber inspection bureau or fir, subalpine no. 2 southern pine inspection bureau or fir, subalpine standard west coast lumber inspection bureau or hemlock, eastern no. 2 northeastern lumber manufacturers association or hemlock, western standard west coast lumber inspection bureau or larch no. 2 southern pine inspection bureau or pine, idaho white no. 2 southern pine inspection bureau or pine, lodgepole no. 2 southern pine inspection bureau or pine, ponderosa no. 2 southern pine inspection bureau or pine, norway no. 2 northeastern lumber manufacturers association or pine, southern no. 2 southern pine inspection bureau or pine, sugar no. 2 southern pine inspection bureau or redwood no. 2 west coast lumber inspection bureau or spruce, eastern no. 2 northeastern lumber manufacturers association or spruce, sitka standard west coast lumber inspection bureau

**Moisture Content Retention Percentage:**

19.0

**Random Length:**

8 feet and longer, permitting 5 pct 8-9 feet and requiring 50 pct 14 feet and longer

**Width-location And Measuring Method:**

4.000 inches specified

**Measuring Method And Length:**

6.000 feet random

**Surface Condition Degree:**

Surfaced two sides or surfaced four sides

**Thickness-location And Measuring Method:**

4.000 inches specified

**Typical Wood Products Use:**

Low cost construction, blocking, boxes, crates and dunnage

**Special Features:**

Seasoning process, air or kiln dried, surface condition, dressed

**Supplementary Features:**

Unit of issue-bf

**Specification Data:**

81348-mm-l-751 government specification

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0