

View Online at <https://aerobasegroup.com/nsn/5510-00-220-6248>

Species-grade And Grading Association:

Any acceptable no. 3 northeastern lumber manufacturers association or any acceptable no. 3 northern hardwood and pine manufacturers association or any acceptable no. 3 west coast lumber inspection bureau or any acceptable no. 3 western wood products association or pine, southern no. 3 southern pine inspection bureau or redwood no. 3 redwood inspection service

Moisture Content Retention Percentage:

19.0

Random Length:

6 feet and longer w/a maximum of 10 pct to be 6-9 feet and min of 40 pct 14 feet and longer

Width-location And Measuring Method:

10.000 inches specified

Measuring Method And Length:

6.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

2.000 inches specified

Typical Wood Products Use:

Low cost construction, blocking, boxes, crates and dunnage

Supplementary Features:

Unit of issue-bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

lii table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0