

View Online at <https://aerobasegroup.com/nsn/5510-00-243-9145>

Species-grade And Grading Association:

Douglas fir ungraded unrecognized

Moisture Content Retention Percentage:

22.0

Width-location And Measuring Method:

3.250 inches specified

Measuring Method And Length:

10.000 feet specified

Thickness-location And Measuring Method:

4.250 inches specified

Typical Wood Products Use:

Line construction poles

Special Features:

Tar creosote preservative per federal specification tt-w-556 table 1

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0