

View Online at <https://aerobasegroup.com/nsn/5510-00-267-2278>

Random Width:

3 in. And wider permitting a maximum of 5 pct of the contract line item quantity to be furnished in widths of 3 in. And requiring a min of 60 pct of the item quantity to be furnished in widths 6 in. And wider

Species-grade And Grading Association:

Maple, hard 1 common national hardwood lumber association

Moisture Content Retention Percentage:

12.0

Random Length:

4 ft and longer permitting a maximum of 10 pct of the contract line item quantity to be furnished in lengths 4 through 7 ft; of which 1/2 may be 4 and 5 ft lengths and requiring a min of 30 pct of the item quantity to be furnished in lengths 14 ft and longer

Width-location And Measuring Method:

3.000 inches random

Measuring Method And Length:

4.000 feet random

Thickness-location And Measuring Method:

1.500 inches specified

Typical Wood Products Use:

Cutting grades for remanufacture

Special Features:

Rough. Air or kiln dried

Supplementary Features:

Typical use--for remaboard foot

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0