

View Online at <https://aerobasegroup.com/nsn/5510-00-267-2338>

Maximum Grain Slope:

Any acceptable

Random Width:

6 in. And wider, requiring 60 pct 10 in. And wider

Species-grade And Grading Association:

Mahogany ship decking unrecognized

Moisture Content Retention Percentage:

15.0

Random Length:

8 feet and longer, requiring 60 pct 16 feet and longer

Width-location And Measuring Method:

6.000 inches tapered end random

Measuring Method And Length:

12.000 feet random

Surface Condition Degree:

Rough-unsanded full length

Thickness-location And Measuring Method:

1.250 inches specified

Typical Wood Products Use:

Decking and planking for ships

Special Features:

Alaska-ceder or port-orford-ceder may be substituted for mahogany planking and @decking, see nsns5510-220-4702, 5510-220-4706, 5510-220-4711 and 5510-220-4716 for possible substitutes

Supplementary Features:

Btypical use--for boat and ship construction, replacement of bright work where appearance governs and for structural applications where hull plans specify /mahogany only/, unit @of issue--board foot

Specification Or Standard:

Pd class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0