

View Online at <https://aerobasegroup.com/nsn/5510-00-267-2379>

Species-grade And Grading Association:

Hardwood no. 3 construction boards national hardwood lumber association and hardwood 3a common national hardwood lumber association and hardwood 3b common national hardwood lumber association

Random Length:

6 ft and longer

Width-location And Measuring Method:

4.000 inches specified

Measuring Method And Length:

6.000 feet random

Surface Condition Degree:

Rough-unsanded full length

Thickness-location And Measuring Method:

1.000 inches specified

Typical Wood Products Use:

Dunnage

Supplementary Features:

Typical use--for ship dunnage, unit of issue--board foot

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0