

View Online at <https://aerobasegroup.com/nsn/5510-00-267-2413>

Random Width:

4 in. And wider, requiring 60 pct 6 in. Or wider

Species-grade And Grading Association:

Mahogany 1 common national hardwood lumber association

Moisture Content Retention Percentage:

12.0

Random Length:

6 feet and longer, permitting 15 pct 6 or 7 feet and requiring 30 pct 14 feet or longer

Width-location And Measuring Method:

4.000 inches random

Measuring Method And Length:

6.000 feet random

Surface Condition Degree:

Rough-unsanded full length

Thickness-location And Measuring Method:

2.000 inches specified

Typical Wood Products Use:

Cutting grades for remanufacture

Special Features:

Air or kiln dried

Supplementary Features:

Typical use--mahogany cutting grades for remanufacture, unit of issue--board foot

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0