

View Online at <https://aerobasegroup.com/nsn/5510-00-270-6031>

Treatment Type:

Preservative, tt-w-572

Preservative Solution Type:

Copper-8-quinolinolate

Species-grade And Grading Association:

Oak, red ungraded unrecognized or oak, white ungraded unrecognized

Moisture Content Retention Percentage:

Between 6.0 and 12.0

Width-location And Measuring Method:

11.500 inches specified

Measuring Method And Length:

19.072 feet specified

Thickness-location And Measuring Method:

1.120 inches specified

Typical Wood Products Use:

Preservative treated high quality flooring or exterior decking

Service Usage:

Ready-to-use solutions by simple nonpressure methods

Special Features:

Left side

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0

Mil-std (military Standard):

Mil-h-3912 spec.