

View Online at <https://aerobasegroup.com/nsn/5510-00-274-4993>

Random Width:

4 in. And wider, permitting 10 pct 4-5 in. And requiring 25 pct 10 in. And wider

Species-grade And Grading Association:

Ash vehicle number national hardwood lumber association or oak, red vehicle number national hardwood lumber association or oak, white vehicle number national hardwood lumber association

Moisture Content Retention Percentage:

27.0

Random Length:

8-16 feet permitting 25 pct 8-11 feet of which one half may be 8-9 feet

Width-location And Measuring Method:

4.000 inches random

Measuring Method And Length:

8.000 feet random

Surface Condition Degree:

Surfaced two sides

Thickness-location And Measuring Method:

3.000 inches specified

Typical Wood Products Use:

Vehicle lumber for construction and repair of vehicle bodies

Supplementary Features:

Typical use--for construction and repair of vehicles bodies, unit of issue--board foot

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0